


residential and commercial spaces. Engineered to perform in high-humidity conditions, the boards offer superior structural integrity with minimal swelling or deformation, even in challenging environments.

With a range of premium finishes - including raw, sanded, melamine, and veneer, PSB® Ultra enhances the beauty of parquet flooring, ensuring a polished and elegant appearance.

WHY PSB® ULTRA FLOORING?






- PSB® Ultra is designed for heavy-duty applications, ensuring both longevity and performance.
- The exceptional moisture resistance of PSB® Ultra ensures that its structural integrity is maintained, even in challenging weather conditions. Known for its robustness, PSB® Ultra is an ideal choice for heavy-duty applications, capable of bearing significant loads without compromising performance.
- PSB® Ultra delivers high performance with a modulus of elasticity of 3,500 Newtons per square
 millimeter (N/mm²) and a modulus of rupture ranging from 18 to 22 Newtons per square millimeter
 (N/mm²).
- PSB® Ultra offers superior strength and stability, even in high-humidity conditions.
- The screw hold capacity of PSB® Ultra is significantly higher compared to other solutions, with edge hold at 1,350 Newtons (N) and face hold at 1,650 Newtons (N). Mechanically, this means that the board can be reused many times using the same hole.

SPECIFICATIONS

Modulus of Rupture	18 – 22 N/mm2
Modulus of elasticity	3,500 N/mm2
Internal Bonding	0.40 – 0.50 N/mm2
Thickness Swelling	12%
Width	1,200 – 1,250 mm
Length	1,830 – 3,048 mm
Thickness	9 – 25 mm


CUSTOMIZABLE FINISHES







Premium Surface (Putty) Finishing





BEST PRACTICES FOR PSB® ULTRA FLOORING?

- To ensure optimal performance in humid conditions, it is recommended to apply a coating to the boards. This will enhance their durability and resilience against moisture, thereby maintaining their reliability in load-bearing applications.
- (i) When resizing the boards (cutting to different or smaller dimensions), it is essential to coat the newly exposed edges.
- *i* For components being fastened, such as beams, rafters, joists, and trusses, pre-drilling is essential. The diameter of the pre-drilled hole should be smaller than the screw diameter to ensure effective engagement of the screw threads.
- During transportation and storage, it is important to protect the PSB® boards from direct exposure to water droplets and precipitation on their edges and surfaces. Ensure that adequate protective covers are provided to maintain their integrity.
- For fastening, it is recommended to use screws, nails, or staples with a length at least 2.5 times the thickness of the board, but not less than 75-50 mm. Fastening should be carried out at intervals of 300-150 mm on intermediate supports (depending on roof pitch), 150 mm along board joints, and 100 mm along roof edges.

TECHNICAL DATA SHEET

PSB® ULTRA FLOORING	TEST METHOD	UNIT	REQUIREMENT		
F3B OLINATILOONING			BOARD THICKNESS RANGE (MM)		
TESTINGS			9 to 10	> 10 to 16	> 16 to 25
Bending strength - major axis	EN 310	N/mm²	22	20	18
Bending strength - minor axis	EN 310	N/mm²	11	10	9
Modulus of elasticity in bending - major axis	EN 310	N/mm²	3500	3500	3500
Modulus of elasticity in bending - minor axis	EN 310	N/mm²	1400	1400	1400
Internal bond	EN 319	N/mm²	0.50	0.45	0.40
Swelling in thickness - 24H immersion	EN 317	%	12	12	12
IB After Boiling test	EN 1087-1	N/mm²	0.17	0.15	0.13



Al Talah Board Manufacturing Company Ltd. KEZAD, Abu Dhabi, UAE P.O. Box: 41543

PHONE & FAX

Tel.: +971 2 246 7042 Fax: +971 2 671 7933

ONLINE

Email: info@desertboard.ae Website: www.desertboard.ae



MADE IN THE UAE

⊕desertboard.ae